

Technical Data

	Test Method	Unit	Value
General Properties			
Density	DIN EN ISO 1183-1	g/cn3	0,97
Water absorption	DIN EN ISO 62	%	<0,05
Flammability (Thickness 3mm / 6mm)	UL 94		HB
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	32
Elongation at break	DIN EN ISO 527	%	>50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1200
Notched impact strength (charpy)	DIN EN ISO 179	kJ/m	6
Shore hardness	DIN EN ISO 868	Scale D	65
Thermal properties			
Melting temperature	ISO 11357-3	°C	135
Thermal conductivity	DIN 52612-1	W / (m * K)	0,40
Thermal capacity	DIN 52612	kJ / (kg * K)	1,90
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ K ⁻¹	150-230
Service temperature, long term	Average	°C	-10 ...80
Service temperature, short term (max.)	Average	°C	100
Heat deflection temperature	DIN EN ISO 306, Vicat B	°C	67
Electrical properties			
Dielectric constant	IEC 60250		2,4
Dielectric dissipation factor (10Hz)	IEC 60250		0,0004
Volume Resistivity	IEC 60093	Ω*cm	>10 ¹⁴
Surface Resistivity	IEC 60093	Ω	>10 ¹⁴
Comparative tracking index	IEC 60112		600
Dielectric strength	IEC 60243	kV/mm	45

Remember...

In between uses there is no need to store indoors. The material we use is guaranteed for 10 years and is fully recyclable, it was developed for external use so can be left outside between uses.

